



DATA SHEET

GRAYING PARQUET FOR NEW OR ANCIENT WOOD 0848 MANUAL APPLICATION

A single application gets by oxidation one skates grey on the oak and the tannic wood, the red oak and the American white oak.

PREPARATION

- NEW PARQUET The wood must be sanded and dusted.
- ANCIENT PARQUET The wood must be sanded, more have no track of varnish, wax and dust it.

IMPLEMENTATION

Mix 150g of powder (3 firmly packed measures) in 1 liter of water, indeed mix, let base 5 - 10 min. Applies by pulverizings or to the brush in plentiful and regular coats, after drying one eliminate the coat of white dust by means of a green abrasive or of a mono-brush provided with a PAD, then we inhale the dust.

FINISH

The parquet so prepared is ready to receive a varnished or polished finish.

VARNISH

It is necessary to apply at first an INSULATING BOTTOM 0219 in one coat which will allow to preserve the light gray color, then we apply our VARNISH.

Consumption : 7 - 9 m² in approximately the liter according to the porosity of the ground.

Packing : 600 g (= 4 L) - 5 kg (= 33 L) – 30 kg (= 200 L)

Honest given information but not engaging our responsibility.